

# Sandvik SAF 2507 for wirelines

## (Wire)

Sandvik SAF 2507 is a super-duplex (austenitic-ferritic) stainless steel for service in highly corrosive conditions. The grade is characterized by:

- Excellent resistance to stress corrosion cracking (SCC) in chloride-bearing environments
- Excellent resistance to pitting and crevice corrosion
- High resistance to general corrosion
- High resistance to erosion corrosion and corrosion fatigue
- High mechanical strength and correspondingly high breaking loads in its slickline wire product form

### STANDARDS

- UNS S32750
- EN number 1.4410
- EN name X 2 CrNiMoN 25-7-4
- SS 2328

### CHEMICAL COMPOSITION (NOMINAL) %

C	Si	Mn	P	S	Cr	Ni	Mo	Others
max.	max.	max.	max.	max.				
0.030	0.8	1.2	0.035	0.015	25	7	4	N=0.3

### CORROSION RESISTANCE

#### General corrosion

Sandvik SAF 2507 is highly resistant to corrosion by organic acids, e.g. experience less than 0.05 mm/year in 10% formic and 50% acetic acid where ASTM 316L has a corrosion rate higher than 0.2 mm/year. Pure formic acid, see Figure 2.

Sandvik SAF 2507 remains resistant even in contaminated acids. Figure 3 and Figure 4 show results from tests of Sandvik SAF 2507 and various stainless steels and nickel alloys in acetic acid contaminated with chlorides which in practice are frequently present in processes.




Figure 2. Isocorrosion diagram in formic acid. The curves represent a corrosion rate of 0.1 mm/year (4 mpy) in stagnant test solution.




Figure 3. Corrosion rate of various alloys in 80% acetic acid with 2000 ppm chloride ions at 90°C (194°F).




Figure 4. Corrosion rate of various alloys in concentrated acetic acid with 200 ppm chloride ions.

Practical experience with Sandvik SAF 2507 in organic acids, e.g. in terephthalic acid plants, has shown that this alloy is highly resistant to this type of environment. The alloy is therefore a competitive alternative to high alloyed austenitics and nickel alloys in applications where standard austenitic stainless steels corrode at a high rate.

Resistance to inorganic acids is comparable to, or even better than that of high alloy austenitic stainless steels in certain concentration ranges. Figures 5 to 7 show isocorrosion diagrams for sulphuric acid, sulphuric acid contaminated with 2000 ppm chloride ions, and hydrochloric acid, respectively.




Figure 5. Isocorrosion diagram in naturally aerated sulphuric acid. The curves represent a corrosion rate of 0.1 mm/year (4 mpy) in a stagnant test solution.




Figure 6. Isocorrosion diagram, 0.1 mm/year (4 mpy) in a naturally aerated sulphuric acid containing 2000 ppm chloride ions.




Figure 7. Isocorrosion diagram in a hydrochloric acid. The curves represent a corrosion rate of 0.1 mm/year (4 mpy) in stagnant test solution.

#### Pitting and crevice corrosion

The pitting and crevice corrosion resistance of stainless steel is primarily determined by the content of chromium, molybdenum and nitrogen. The manufacturing and fabrication practice, e.g. welding, are also of vital importance for the actual performance in service.

A parameter for comparing the resistance to pitting in chloride environments is the PRE number (Pitting Resistance Equivalent). The PRE is defined as, in weight-%  $PRE = \%Cr + 3.3 \times \%Mo + 16 \times \%N$

For duplex stainless steels the pitting corrosion resistance is dependent on the PRE value in both the ferrite phase and the austenite phase, so that the phase with the lowest PRE value will be limiting for the actual pitting corrosion resistance. In Sandvik SAF 2507 the PRE value is equal in both phases, which has been achieved by a careful balance of the elements.

The minimum PRE value for Sandvik SAF 2507 wirelines is 41.

#### Stress corrosion cracking

Sandvik SAF 2507 has excellent resistance to chloride induced stress corrosion cracking (SCC). Figure 8 clearly demonstrates that Sandvik SAF 2507 has better SCC resistance in chloride solutions in comparison with several duplex and austenitic alternative grades in the annealed condition.

There were no signs of SCC in Sandvik SAF 2507 up to 1000 ppm Cl<sup>-</sup>/300°C (572°F) and 10000 ppm Cl<sup>-</sup>/250°C (482°F).

The super-duplex stainless steel Sandvik SAF 2507 has a higher resistance to SCC in in sour environments in oil and gas production than lower alloyed duplex stainless steels. The partial pressure of hydrogen sulphide should not exceed 3 psi (0.20 bar).




Figure 8. SCC resistance in oxygen-bearing (abt. 8 ppm) neutral chloride solutions. Testing time 1000 hours. Applied stress equal to proof strength at testing temperature.

**Erosion corrosion**

The mechanical properties combined with corrosion resistance give Sandvik SAF 2507 a good resistance to erosion corrosion. Testing in sand containing media has shown that Sandvik SAF 2507 has an erosion corrosion resistance better than corresponding austenitic stainless steels. Figure 9 below shows the relative mass loss rate of the duplex Sandvik SAF 2507, Sandvik SAF 2205 and an austenitic 6Mo+N type steel after exposure to synthetic seawater (ASTM D-1141) containing 0.025-0.25% silica sand at a velocity of 8.9-29.3 m/s (average of all tests is shown).




Figure 9. Relative mass loss rate after testing for resistance to erosion corrosion.

**CORROSION FATIGUE**

Duplex stainless steels which have a high tensile strength usually have a high fatigue limit and high resistance to both fatigue and corrosion fatigue.

The high fatigue strength of Sandvik SAF 2507 can be explained by its good mechanical properties, while its high resistance to corrosion fatigue has been proven by fatigue testing in corrosive media.

**FORMS OF SUPPLY**

Sandvik SAF 2507 slicklines are supplied cold drawn and degreased, in continuous lengths, without welds, on metallic spools.

Diameter		Breaking load		Weight	
mm	in.	N	lbf	kg/1000 m	lb/1000 ft
2.083	0.082	5622	1263	26.6	17.8
2.337	0.092	7077	1590	33.5	22.4
2.743	0.108	9753	2192	46.1	30.9
3.175	0.125	13065	2936	61.8	41.4

## MECHANICAL PROPERTIES

Wire in Sandvik SAF 2507 is tested and certified in accordance with a minimum nominal tensile strength. Proof strength is approximately 90% of the tensile strength. Sandvik SAF 2507 is able, therefore, to resist high loads without permanent set of the wire.

### AT 20°C (68°F)

Proof strength, $R_{p0.2}^*$		Tensile strength, $R_m$	
MPa	ksi	MPa	ksi
1485	215	1650	240

\*  $R_{p0.2}$  corresponds to 0.2% offset yield strength.

## PHYSICAL PROPERTIES

Density: 7.8 g/cm<sup>3</sup>, 0.28 lb/in.<sup>3</sup>

## SPECIFIC HEAT CAPACITY

Metric units		Imperial units	
Temperature, °C	J/(kg °C)	Temperature, °F	Btu/(lb°F)
20	490	68	0.12
100	505	200	0.12
200	520	400	0.12
300	550	600	0.13
400	585	800	0.14

## THERMAL CONDUCTIVITY

### METRIC UNITS, W/(M°C)

Temperature, °C	20	100	200	300	400
Sandvik SAF 2507	14	15	17	18	20
ASTM 316L	14	15	17	18	20

### IMPERIAL UNITS, BTU/(FT H °F)

Temperature, °F	68	200	400	600	800
Sandvik SAF 2507	8	9	10	11	12
ASTM 316L	8	9	10	10	12

## THERMAL EXPANSION

Sandvik SAF 2507 has a coefficient of thermal expansion close to that of carbon steel. This gives Sandvik SAF 2507 definite design advantages over austenitic stainless steels in equipment comprising of both carbon steel and stainless steel. The values given below are average values in the temperature ranges.

**METRIC UNITS, X10<sup>-6</sup>/°C**

Temperature, °C	30-100	30-200	30-300	30-400
Sandvik SAF 2507	13.5	14.0	14.0	14.5
Carbon steel	12.5	13.0	13.5	14.0
ASTM 316L	16.5	17.0	17.5	18

**IMPERIAL UNITS, X10<sup>-6</sup>/°F**

Temperature, °F	86-200	86-400	86-600	86-800
Sandvik SAF 2507	7.5	7.5	8.0	8.0
Carbon steel	6.8	7.0	7.5	7.8
ASTM 316L	9.0	9.5	10.0	10.0




Figure 1. Thermal expansion, per°C (30-100°C, 86-210°F).

**RESISTIVITY**

Temperature, °C	μΩm	Temperature, °F	μΩin.
20	0.83	68	32.7
100	0.89	200	34.9
200	0.96	400	37.9
300	1.03	600	40.7
400	1.08	800	43.2

**MODULUS OF ELASTICITY, (X10<sup>3</sup>). METRIC UNITS AND IMPERIAL UNITS**

Temperature, °C	MPa	Temperature, °F	ksi
20	200	68	29.0
100	194	200	28.2
200	186	400	27.0
300	180	600	26.2

**DISCLAIMER:**

Recommendations are for guidance only, and the suitability of a material for a specific application can be confirmed only when we know the actual service conditions. Continuous development may necessitate changes in technical data without notice. This datasheet is only valid for Sandvik materials.